

Compound TR6960

SEBS

Typical properties	Unit	Standard	Value
Packaging	kg / bag		25
Hardness	°ShA	DIN 53505	40
MFI (190 °C – 2.16 kg)	g/10'	ASTM D1238-90b	2.0
Specific Gravity	g/cm ³	DIN 53550	0.98
Physical form			Cylindrical granules
Colour			Black

Mechanical properties MD/CD	Unit	Standard	Value
Tensile strength	MPa	DIN 53504	4.1/5.8
Module 100%	MPa	DIN 53504	1.0/0.8
Module 200%	MPa	DIN 53504	1.7/1.3
Module 300%	MPa	DIN 53504	2.4/1.9
Elongation at break	%	DIN 53504	20/18
Temperature profile		Hopper–180 °C-190 °C-210 °C-nozzle	
Applications		Extrusion of profiles injection moulding products	